

1.PRODUCT DESCRIPTION

PRODUCT NAME	MAX BAU ACORNPlex
SIZE(MM)	1250 × 2500
THICKNESS(MM)	18MM
NUMBER OF LAYERS	11 LAYERS
KINDS OF FILM COLOR	DYNEA BROWN FILM
PROCESSING OF EDGE	BROWN COLOR
MATERIALS	FULL FRESH STANDARD PINE
DENSITY	550 KG/M ³
GLUE	MELAMINE W.B.P GLUE
MOISTURE CONTENT	8%-12%
HOT-PRESS TIMES	TWO TIMES HOT-PRESS&SANDING
REUSE	10 TIMES BY FORMWORK

2.TECHNICAL SPECIFICATION

NO	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8.5%	CHECK OUT
2	DENSITY		KG/M³	EN 323	550	CHECK OUT
3	BONDIN QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.43 MIN:0.76	CHECK OUT
		DAMAGE RATE	%		79%	
4	BENDING MODULUS OF ELASICITY	LONGITUDINAL	MPA	EN 310	5639	CHECK OUT
		LATERAL			5352	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		53.54	CHECK OUT
		LATERAL			44.46	

3. TESTING REPORT

LABORATORY TEST



INSPECTION PICS



"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.