

1.PRODUCT DESCRIPTION

PRODUCT NAME	MAX BAU FORTUNEPLEX
SIZE(MM)	1250 × 2500
THICKNESS(MM)	20MM
NUMBER OF LAYERS	6 LAYERS
KINDS OF FILM COLOR	BLACK FILM
PROCESSING OF EDGE	BROWN COLOR
MATERIALS	3+3 WHOLE PINE VENEER
DENSITY	600 KG/M ³
GLUE	MR GLUE
MOISTURE CONTENT	8%-14%
HOT-PRESS TIMES	ONE TIMES HOT-PRESS
REUSE	5-6 TIMES BY FORMWORK

2.TECHNICAL SPECIFICATION


NO .	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8.2 %	CHECK OUT
2	DENSITY		KG/M³	EN 323	600	CHECK OUT
3	BONDIN QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.34 MIN:0.73	CHECK OUT
		DAMAGE RATE	%		67%	
4	BENDING MODULUS OF ELASICITY	LONGITUDINAL	MPA	EN 310	4456	CHECK OUT
		LATERAL			4345	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		49.75	CHECK OUT
		LATERAL			39.25	

3. TESTING REPORT

LABORATORY TEST



INSPECTION PICS



"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.