

STARFLOOR CLICK SOLID 55

TECHNICAL DATA

Certification & classification	Standards	Starfloor Click Solid 55
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	Domestic: 23 Commercial: 33
Technical characteristics		
Total thickness	EN ISO 24346	5.0mm
Wear layer thickness	EN ISO 24340	0.55 mm
Total weight	EN ISO 23997	8850 g/m ²
Wear layer binder content	EN ISO 10582	Type I
Dimensions	EN ISO 24342	Planks 121,1 x 19,05cm = 7/box = 1,61m ² /box 149,1 x 24,05cm = 4/box = 1,43m ² /box Tiles 60,1x32,38cm = 8/box = 1,56m ² /box 99,1x49,05cm = 3/box = 1,46m ² /box
Surface treatment (PUR)	-	Topcoat PU
High definition Digitally Printed	-	Yes on Starfloor Click Solid 55 DP references
Embossing in Register	-	Yes on Starfloor Click Solid 55 EIR references
Technical performances		
Dimensional stability standard value	EN ISO 23999	≤ 0,15 %
Dimensional stability average measured value	EN ISO 23999	0,10%
Curl resultant to heat	EN ISO 23999	≤ 1 mm
Reaction to fire	EN 13501-1	Bfl-s1 loose laid over concrete substrate
Residual indentation	EN ISO 24343-1	≤ 0,10 mm
Furniture leg	EN 424	No damage
Castor chair	ISO 4918 - EN 425	No damage
Impact sound reduction	EN ISO 717-2	ΔLw = 5 dB
Reduction of in-room impact noise	EN ISO 31-074	Class C (Ln,e,w < 85 dB)
Thermal resistance	EN ISO 10456	0,05 m ² K/W
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6
Chemical resistance	EN ISO 26987	Not affected (0)
Slip resistance	DIN 51130 EN 13893	R9 / R10 depending on embossing μ ≥ 0,30
Peeling resistance	EN ISO 24345	≥ 50N / 50mm
Underfloor heating	-	Suitable - max. 27 °C
Environmental TAG		
VOC emission	ISO 16000-9	≤ 10μg/m ³
Recycled content	-	35%
Recyclable	-	100%
Plasticizer	-	Phthalate-free
CE Marking		
DoP number	-	No 0197- 0010-DoP-2021-02

According to the European Regulation N° 305/2011 for CE Marking, the Declaration of Performance n° 0197- 0010-DoP-2021-02 is available on our website www.tarkett.com
Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

