

HUMIDITY BARRIER SHEET



The polyethylene sheet should be laid under the insulating panel, thus acting as a humidity barrier.



Package	Code
custom-made	1901100
100 m ²	1901250

Features	Standard	Value		U.M.	Tolerance
		1901100	1901250		
Width		400	200	cm	± 3 %
Length		100	50	m	± 1.5 %
Thickness	ISO 4593-93	180		μ	± 10 %
Density	ASTM D 1505	0.923		g/cm ³	± 0.005 %
Softening temperature	ASTM D 1525	103		°C	
Water vapour diffusion resistance factor μ	EN 12086	89900		μ	

