

	Technical Characteristic KAI/KOS FISA TEHNICA	ODU 16.07.05(9/0)
---	--	------------------------------------

Model „Denver“
Internal code: 6425KA; 6427KA
Type Porcelain Tiles GL,
Group Bla, Nominal size 150x900x8.0 mm

Characteristics/ caracteristici Group Bla, Annex G	Tolerance EN 14411:2016, %	Tolerance EN14411:2016, mm	Request values/Valori conform standard	Measured in KAI laboratory/Masuratori in laborator Kai	Testing method/ Metoda de lucru										
1.Work size, mm Length/widthLungime /Latime, mm	±0.6/max±2mm	±0.9/±2.0	150 x 900	<table><tr><td>1K</td><td>149.0x896.8</td></tr><tr><td>2K</td><td>149.5x898.4</td></tr><tr><td>3K</td><td>150.0x900.0</td></tr><tr><td>4K</td><td>150.5x901.6</td></tr><tr><td>5K</td><td>151.0x903.2</td></tr></table>	1K	149.0x896.8	2K	149.5x898.4	3K	150.0x900.0	4K	150.5x901.6	5K	151.0x903.2	EN ISO 10545-2
1K	149.0x896.8														
2K	149.5x898.4														
3K	150.0x900.0														
4K	150.5x901.6														
5K	151.0x903.2														
2.Thickness/ Grosimea, mm	±5/max±0.5mm	±0.43	8.0±0.45 mm	7.8 – 8.0 mm	EN ISO 10545-2										
3. Straightness of sides/ Liniaritatea muchiei, mm	±0.5/max±1.5mm	±0.75/±1.50	±0.8 mm	-0.10 – 0.20mm	EN ISO 10545-2										
4. Rectangularity/ Rectangularitate , mm	±0.5/max±2mm	±0.75/±2.0	±0.8 mm	±0.8 mm	EN ISO 10545-2										
5. Centre curvature/ Curbura centrala, mm	±0.5/max±2mm	±2.0	CC – 0.6 mm; CV + 1.5 mm	+0.33 - +1.00 mm	EN ISO 10545-2										
6. Edge curvature/ Curbura laterala, mm	±0.5/max±2mm	±0.75/±2.0	CC – 0.6 mm; CV + 1.5 mm	+0.58 – 1.03 mm	EN ISO 10545-2										
7. Warpage/ Deformarea, mm	±0.5/max±2mm	±2.0	CC – 0.6 mm; CV + 1.5 mm	CC – 0.6 mm; CV + 1.5 mm	EN ISO 10545-2										
8. Surface quality/ Calitatea suprafetei	≥95% without defects	≥95% without defects	≥98% without defects	Pass	EN ISO 10545-2										
9.Water absorption Absorbția de apa, %	≤0,5% Individual ≤0,6%	≤0,5% Individual ≤0,6%	≤0,3%	0.07 – 0.21%	EN ISO 10545-3										
10.Modulus of rupture Rezistența mecanică, N/mm²	≥35N/mm² individual≥32N/m m²	≥35N/mm² individual≥32N/m m²	≥35N/mm²	Average: 58 N/mm²	EN ISO 10545-4										
11. Breaking strength Forța de rupere, N	≥ 1300N	≥ 1300N	≥ 1300N	Average: 1992 N	EN ISO 10545-4										
12.Determination of surface abrasion for glazed tiles/Rezistența la abraziune	the class of abrasive resistance and the number of cycles are declared by producer	the class of abrasive resistance and the number of cycles are declared by producer	Declared value	6425 – 3/750 6427 – 3/750	EN ISO 10545-7										

13.Crazing resistance, glazed tiles/ Resitenta la crapaturi pentru placi glazurate	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-9
14.Resistance for household chemicals and swimming pool salts/ Rezistenta la solutiile de uz casnic si saruri de piscina	Min class B	Min class B	Min class B	GA	EN ISO 10545-13
15.Resistance to the low concentration acids and alkalis/ Rezistenta la acizi si baze de concentratie slaba	Declared value	Declared value	Declared value	GLA	EN ISO 10545-13
16. Resistance to the high concentration acids and alkalis/ Rezistenta la acizi si baze de concentratie mare	Declared value	Declared value	Declared value	GHA	EN ISO 10545-13
17.Stain resistance Rezistenta la patare	Min class 3	Min class 3	Min class 5	class 5	EN ISO 10545-14
18. Frost resistance Rezistenta la inghet	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-12
19. Slipperiness Rezistenta la alunecare	Declared value	Declared value	Declared value	PTV 36+ Dry PTV 0-24 Wet	BS 7976
20. MOHS Rezistenta la zgariere	Declared value	Declared value	Declared value	8	EN 101:1991

Date: 02.10.2024

