



KERATILE, S.L.U.
Pol. Ind. Casablanca. Calle del Ferrocarril, 4. 12593 Moncofar.
Castellon, Spain . www.keratile.es

MODELO / MODEL		QUARTZ SERIES MT (Brown, Grey, White)		
FOTO / PICTURE (ORIENTATIVE)		 P.E. QUARTZ BROWN MT 37X75	 P.E. QUARTZ GREY MT 37X75	 P.E. QUARTZ WHITE MT 37X75
FORMATO / SIZE		37 X 75 cms.		
GRUPO / GROUP		Bla		
TIPO / TYPE		PORCELANICO ESMALTADO / Glazed Porcelain Tile		
DESCRIPCION DEL TEST / TEST DESCRIPTION		VALOR DEL TEST / TEST VALUE	KERATILE	NORMA / STANDARD
ABSORCIÓN DE AGUA / WATER ABSORPTION		AA < 0,5%	Cumple / Passed	UNE-EN-ISO 10545-3
FUERZA DE ROTURA / BREAKING STRENGTH		> 1300 N	Cumple / Passed	UNE-EN-ISO 10545-4
RESISTENCIA A LA FLEXIÓN / RESISTANCE OF FLEXION		> 35 N/mm2	Cumple / Passed	UNE-EN-ISO 10545-4
ABRASION SUPERFICIAL / SURFACE ABRASION		Clase / Class	PEI IV	UNE-EN-ISO 10545-7
RESISTENCIA AL CUARTEO / CRACKING RESISTANCE		Requerido / Requested	Cumple / Passed	UNE-EN-ISO 10545-11
RESISTENCIA A LA HELADA / FROST RESISTANCE		Requerido / Requested	Cumple / Passed	UNE-EN-ISO 10545-12
RESISTENCIA QUIMICA / CHEMICAL RESISTANCE	(PRODUCTOS DOMESTICOS Y DE PISCINA / Domestic & Swimming Pool Products)	Mínimo / Minimum GB	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LOS ACIDOS / ACID RESISTANCE		GHA	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LAS BASES / ALKALINE RESISTANCE		GHA	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LAS MANCHAS / RESISTANCE TO STAINS		Mínimo / Minimum Class 3	Cumple / Passed	UNE-EN-ISO 10545-14
RESISTENCIA AL DESLIZAMIENTO / SLIP RESISTANCE		Metodo Disponible / Available Method	Class 1	UNE-ENV 12633:2003
SLIP RESISTANCE		D.C.O.F.	>0,42	ANSI A137. 1:2012. 9.6
RESISTENCIA AL RAYADO / HARDNESS (MOHS)		Mínimo / Minimum 3	Cumple / Passed	EN 101

KERATILE S.L.U.
 CIF B-12943338
 Calle del Ferrocarril, 4
 12593 Moncofa (Castellón) Spain
 Tel. +34 964 584 068 / Fax +34 964 584 070