

THERMO-TEK LM ECO ALU (LMH ALUR)



January 2018

APPLICATION RANGE











DESCRIPTION

Thermo-teK LM Eco ALU is a mat with formaldehyde-free binding material consisting of individual mineral wool strips (lamella) that are bonded on the one side to a tear-resistant, glass mesh reinforced aluminium foil.

PERFORMANCE

Service temperature facing side max	80 ℃
Service temperature mineral wool max	250 °C
Reaction to fire	Al
Minimum density	35 kg/m³
Declaration of performance	http://dopki.com/ T4305MPCPR

Sign	Sign Description/data				Unit	Standard		
9	10	50	100	150	200	250	°C	
λ	0,037	0,044	0,056	0,070	0,088	0,109	W/(mK)	DIN EN 12667
-	≤ 10					ppm	EN 13468	
W _P	≤1					kg/m²	EN 1609	
S _d	100					-	-	
-	No emissions by lacquering disturbing sustances					-	-	
-	≥ 1000					°C	DIN 4102-17	
$\sigma_{_{ m m}}$	≥ 10					N/mm²	-	
C _p	1030					kJ/(m²K)	EN ISO 10456	
-	MW-EN14303-T4-ST(+)250-WS1-MV1-CL10				-	EN 14303		
	9 λ - W _p S _d -	9 10 λ 0,037 - W _p S _d - No	9 10 50 λ 0,037 0,044 - W _P 5 _d - No emissions - σ _m C _p	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	$\frac{9}{\lambda}$ 10 50 100 150 $\frac{1}{\lambda}$ 0,037 0,044 0,056 0,070 $\frac{1}{\lambda}$ 0 0,037 0,044 0,056 0,070 $\frac{1}{\lambda}$ ≤ 10 $\frac{1}{\lambda}$ 100 $\frac{1}{\lambda}$ 100 $\frac{1}{\lambda}$ 100 $\frac{1}{\lambda}$ 100 $\frac{1}{\lambda}$ 1000 $\frac{1}{\lambda}$ 1000 $\frac{1}{\lambda}$ 1000 $\frac{1}{\lambda}$ 1030	$\frac{9}{\lambda}$ 10 50 100 150 200 $\frac{1}{\lambda}$ 0,037 0,044 0,056 0,070 0,088 $\frac{1}{\lambda}$ = 10 $\frac{1}{\lambda}$	$\begin{array}{ c c c c c c } \hline 9 & 10 & 50 & 100 & 150 & 200 & 250 \\ \hline \lambda & 0,037 & 0,044 & 0,056 & 0,070 & 0,088 & 0,109 \\ \hline - & & & \leq 10 \\ \hline W_{\rm p} & & \leq 1 \\ \hline S_{\rm d} & & 100 \\ \hline - & No \ emissions \ by \ lacquering \ disturbing \ sustances \\ \hline - & & \geq 1000 \\ \hline G_{\rm m} & & \geq 10 \\ \hline C_{\rm p} & & 1030 \\ \hline \end{array}$	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$

Declared material properties are obtained in the production process and ensured by the factory production control in accordance with the European Standard at the time of manufacture. Observing storage and handling guidelines will maintain performance within published tolerances.

CERTIFICATE













THERMO-TEK LM ECO ALU



January 2018

ADDITIONAL INFORMATION

Application

The product is recommended for thermal, fire and sound insulation of the defined applications within technical insulation.

Pipe lines, Circular and rectangular air ducts, Heat storage tanks

Handling

Our products are easy to handle and easy to install. It is supplied packaged in cardboard boxes or wrapped in foil (depending on the product) which are designed for short term protection only. Further product information is mentioned on every pack.

Storage

For longer term protection on site, it is recommended to store the product either indoors or under a roof and off the ground.

Product features

Thickness	20mm-140mm
Width	500 mm
Length	1.000mm-10.000mm



Knauf Insulation mineral wool products with ECOSE® Technology benefit from a formaldehyde-free binder made from rapidly renewable bio-based materials instead of petroleum-based chemicals. The technology has been developed for Knauf Insulation's mineral wool products, enhancing their environmental credentials without affecting the thermal, acoustic or fire performance. Insulation products made with ECOSE® Technology contain no dye or artificial colours – the colour is completely natural.

Knauf Insulation d.o.o

Varaždinska 140 42220 Novi Marof Croatia

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof. The publisher and editors will be grateful for improvement suggestions and details of possible errors pointed out.